

Zytel® 101F NC010

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 101F NC010 is an internally lubricated polyamide 66 resin for injection molding. It was developed for fast cycles and high productivity.

Product information

Resin Identification	PA66	ISO 1043
Part Marking Code	>PA66<	ISO 11469
ISO designation	ISO 16396-PA66,,M1G1NR,S14-030	

Rheological properties

	dry/cond.		
Viscosity number	150 / *	cm ³ /g	ISO 307, 1628
Molding shrinkage, parallel	1.4 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4 / -	%	ISO 294-4, 2577
Postmolding shrinkage, normal, 48h at 175 °F	0.1 / *	%	ISO 294-4
Postmolding shrinkage, parallel, 48h at 175 °F	0.2 / *	%	ISO 294-4

Typical mechanical properties

	dry/cond.		
Tensile modulus	3100 / 1400	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	82 / 55	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	4.5 / 25	%	ISO 527-1/-2
Nominal strain at break	20 / >50	%	ISO 527-1/-2
Tensile strain at break, 50mm/min	40 / -	%	ISO 527-1/-2
Flexural modulus	2800 / 1200	MPa	ISO 178
Flexural strength	120 / 75	MPa	ISO 178
Tensile creep modulus, 1h	* / 1400	MPa	ISO 899-1
Tensile creep modulus, 1000h	* / 930	MPa	ISO 899-1
Charpy impact strength, 73 °F	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -22 °F	400 / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 73 °F	6 / 13	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -22 °F	4.5 / 3	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 73 °F	5.5 / 11	kJ/m ²	ISO 180/1A
Izod notched impact strength, -22 °F	6.0 / 4.0	kJ/m ²	ISO 180/1A
Izod notched impact strength, -40 °F	5.5 / 3.0 ^[A]	kJ/m ²	ISO 180/1A
Izod impact strength, 73 °F	300 / N	kJ/m ²	ISO 180/1U
Izod impact strength, -22 °F	300 / N ^[A]	kJ/m ²	ISO 180/1U

Zytel® 101F NC010

NYLON RESIN

Hardness, Rockwell, R-scale	121 / 108	ISO 2039-2
Poisson's ratio	0.37 / 0.43	
[A]: Assessed		

Thermal properties

	dry/cond.		
Melting temperature, 18°F/min	262 / *	°C	ISO 11357-1/-3
Glass transition temperature, 18°F/min	70 / 40	°C	ISO 11357-1/-3
Temperature of deflection under load, 260 psi	70 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 65 psi	190 / *	°C	ISO 75-1/-2
Vicat softening temperature, 90°F/h, 11 lbf	240 / *	°C	ISO 306
Ball pressure test	240 / -	°C	IEC 60695-10-2
Coefficient of linear thermal expansion (CLTE), parallel	100 / *	E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	110 / *	E-6/K	ISO 11359-1/-2
Thermal conductivity of melt	0.16	W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	5E-8	m²/s	ISO 22007-4
Specific heat capacity of melt	2790	J/(kg K)	ISO 22007-4
RTI, electrical, 30mil	130	°C	UL 746B
RTI, electrical, 60mil	130	°C	UL 746B
RTI, electrical, 120mil	130	°C	UL 746B
RTI, electrical, 240mil	130	°C	UL 746B
RTI, impact, 30mil	75	°C	UL 746B
RTI, impact, 60mil	75	°C	UL 746B
RTI, impact, 120mil	75	°C	UL 746B
RTI, impact, 240mil	75	°C	UL 746B
RTI, strength, 30mil	85	°C	UL 746B
RTI, strength, 60mil	85 / *	°C	UL 746B
RTI, strength, 120mil	85	°C	UL 746B
RTI, strength, 240mil	85	°C	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 60mil nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.71 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Oxygen index	28 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index, 30mil	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 60mil	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 120mil	960 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 30mil	725 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 60mil	750 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 120mil	800 / -	°C	IEC 60695-2-13
Glow Wire Temperature, No Flame, 40mil	750 / -	°C	IEC 60335-1
Glow Wire Temperature, No Flame, 80mil	725 / -	°C	IEC 60335-1
FMVSS Class	SE		ISO 3795 (FMVSS 302)

Zytel® 101F NC010

NYLON RESIN

Electrical properties

	dry/cond.		
Relative permittivity, 100Hz	3.8/8		IEC 62631-2-1
Relative permittivity, 1MHz	3.6/4.6		IEC 62631-2-1
Dissipation factor, 100Hz	140/-	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	180/1000	E-4	IEC 62631-2-1
Volume resistivity	1E13/1E10	Ohm.m	IEC 62631-3-1
Electric strength	31.5/26	kV/mm	IEC 60243-1
Comparative tracking index	600/-		IEC 60112
Comparative tracking index, 23°C	0/-	PLC	UL 746A

Physical/Other properties

	dry/cond.		
Humidity absorption, 80mil	2.6/*	%	Sim. to ISO 62
Water absorption, 80mil	8.5/*	%	Sim. to ISO 62
Density	1140/-	kg/m³	ISO 1183
Density of melt	970	kg/m³	

Film Properties

	dry/cond.		
Strain at yield, parallel	4.5/*	%	ISO 527-3

VDA Properties

	dry/cond.		
Emission of organic compounds	6.5	µgC/g	VDA 277
Odor test	3	class	VDA 270
Fogging, G-value (condensate)	0.1/*	mg	ISO 6452

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	295 °C
Min. melt temperature	280 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.4 m/s
Mold Temperature Optimum	70 °C
Min. mold temperature	40 °C
Max. mold temperature	95 °C
Hold pressure range	50 - 100 MPa
Hold pressure time	4 s/mm
Ejection temperature	190 °C


Characteristics

Additives	Release agent
-----------	---------------

Zytel® 101F NC010

NYLON RESIN


Dynamic Tensile modulus-temperature (dry)



Zytel® 101F NC010

NYLON RESIN


Dynamic Tensile modulus-temperature (cond.)



Zytel® 101F NC010

NYLON RESIN


Stress-strain (dry)



Zytel® 101F NC010

NYLON RESIN


Stress-strain (cond.)



Zytel® 101F NC010

NYLON RESIN


Secant modulus-strain (dry)



Zytel® 101F NC010

NYLON RESIN

Secant modulus-strain (cond.)



Zytel® 101F NC010

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C
- ✗ Motor oil OS206 304 Ref.Eng.Oil, ISP, 135°C
- ✗ Automatic hypoid-gear oil Shell Donax TX, 135°C
- ✗ Hydraulic oil Pentosin CHF 202, 125°C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Zytel® 101F NC010

NYLON RESIN

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23 °C
- ✗ Sodium Hypochlorite solution (10% by mass), 23 °C
- ✓ Sodium Carbonate solution (20% by mass), 23 °C
- ✓ Sodium Carbonate solution (2% by mass), 23 °C
- ✗ Zinc Chloride solution (50% by mass), 23 °C

Other

- ✓ Ethyl Acetate, 23 °C
- ✗ Hydrogen peroxide, 23 °C
- ✗ DOT No. 4 Brake fluid, 130 °C
- ✗ Ethylene Glycol (50% by mass) in water, 108 °C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23 °C
- ✓ 50% Oleic acid + 50% Olive Oil, 23 °C
- ✓ Water, 23 °C
- ✗ Water, 90 °C
- ✗ Phenol solution (5% by mass), 23 °C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).